

检测报告

编号 : GZIN2304000697CM_CN

日期 : 2023-04-14

页码 : 1 of 3



客户名称: 广州蓝尔迪塑料制品有限公司
 客户地址: 广州市南沙区东涌镇市南路石排段 215 号

样品名称 : 双面镀铝双泡隔热材
 产品规格 : 6mm 厚

以上信息及样品由客户提供及确认, SGS 不承担证实客户提供信息的准确性、适当性和(或)完整性的责任。

SGS 参考号 : CP23-014587
 收样日期 : 2023-04-03
 测试开始时间 : 2023-04-03
 测试结束时间 : 2023-04-14
 测试结果 : 请见下页 (除另有特别说明外, 此报告结果仅对测试样品负责)

通标标准技术服务有限公司广州分公司
 检测中心
 授权签名

杨泳桃 授权签字人



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, Guangdong Province, China 510760
 中国·广东·广州市黄埔区开创大道1501号3栋101房 邮编: 510760

t (86-20) 82155888 www.sgs.com.cn
 f (86-20) 82155888 sgs.china@sgs.com

检测报告

编号 : GZIN2304000697CM_CN

日期 : 2023-04-14


页码 : 2 of 3

结果总结:

序号	测试项目	测试方法	结果	结论
1	导热系数和热阻	ASTM C518-21	见结果	/

备注: 符合: 达到要求
 不符合: 未达到要求
 /: 不下判定

原样照片:



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com
 Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, Guangdong Province, China 510760
 中国·广东·广州市黄埔区开创大道1501号3栋101房 邮编: 510760

t (86-20) 82155888 www.sgs.com.cn
 f (86-20) 82155888 sgs.china@sgs.com

检测报告

编号 : GZIN2304000697CM_CN
 日期 : 2023-04-14
 页码 : 3 of 3

测试项目: 导热系数和热阻

测试方法: ASTM C518-21

测试条件:

试样: 311mm×308mm×6.0mm, 1片

密度: 约 52.3kg/m³

平均温度: 25℃

温差: 20℃

实验室环境条件: (23±2)℃, (50±5)%RH

测试结果:

测试项目	测试结果
导热系数	0.037 W/(m·K)
热阻	0.161 (m ² ·K)/W

备注: 测试结果不应直接与其它条件下的试验结果做对比, 或直接引用于实际情况。

附录信息:

1. 以上测试项目是由 SGS 集团内其他实验室执行的。
2. 本测试报告内容是报告编号为 GZIN2304000697CM 的中文版本。中英文版本如有歧义, 概以英文版为准。
3. 检测报告仅用于客户科研、教学、内部质量控制、产品研发等目的, 仅供内部参考。

***** 报告结束*****

